

PATENT SPECIFICATION

(11)

1 402 010

1 402 010

- (21) Application No. 46891/72 (22) Filed 11 Oct. 1972
 (31) Convention Application No. 188 605 (32) Filed 12 Oct. 1971 in
 (33) United States of America (US)
 (44) Complete Specification published 6 Aug. 1975
 (51) INT. CL.³ G03G 9/00//9/14
 (52) Index at acceptance
 G2H 12 1J4 1JY 1Y 2B 2X 2Y 5A 5D1A 5D1Y 5DY 5Y



(54) ELECTROSTATOGRAPHIC DEVELOPING MATERIAL

(71) We, XEROX CORPORATION of Xerox Square, Rochester, New York 14603, United States of America, a body corporate organized under the laws of the State of New York, United States of America, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:—

This invention relates to an electrostatographic developing material and its use in developing an electrostatic latent image comprised by a surface.

The formation and development of images on the surface of photoconductive materials by electrostatic means is well known. The basic electrophotographic process, as taught by C. F. Carlson in U.S. Patent 2,297,691, involves placing a uniform electrostatic charge on a photoconductive insulating layer, exposing the layer to a light and shadow image to dissipate the charge on the areas of the layers exposed to the light and developing the resulting electrostatic latent image by depositing on the image a finely divided electrosopic material referred to in the art as "toner". The toner will normally be attracted to those areas of the layer which retain a charge thereby forming a toner image corresponding to the electrostatic latent image. This powder image may then be transferred to a support surface such as paper. The transferred image may substantially be permanently affixed to the support surface as by heat. Instead of latent image formation by uniformly charging the photoconductive layer and then exposing the layer to a light and shadow image, one may form the latent image by directly charging the layer in image configuration. The powder image may be fixed to the photoconductive layer if the powder

image transfer step is not desired. Other suitable fixing means such as solvent or overcoating treatment may be substituted for the foregoing heat fixing step.

Several methods are known for applying the electrosopic particles to the electrostatic latent image to be developed. One development method, as disclosed by E. N. WISE in U.S. Patent 2,618,552, is known as "cascade" development. In this method, a developer material comprising relatively large carrier particles having finely divided toner particles electrostatically coated thereon is conveyed to and rolled or cascaded across the electrostatic image bearing surface. The composition of the carrier particles is so selected as to triboelectrically charge the toner particles to their desired polarity. As the mixture cascades or rolls across the latent image bearing surface, the toner particles are electrostatically deposited and secured in positive development processes to the charged portion of the latent image and are not deposited on the uncharged or background portions of the image. Most of the toner particles accidentally deposited in the background areas are removed by the rolling carrier, due apparently, to the greater electrostatic attraction between the toner and the carrier than between the toner and the discharged background. The carrier and excess toner are then recycled. This technique is extremely good for development of line copy images.

Another method for developing electrostatic images is the "magnetic brush" process as disclosed, for example, in U.S. Patent 2,874,063. In this method, a developer material containing toner particles and magnetically attractable carrier particles are carried by a magnet. The magnetic field of the magnet causes alignment of the magnetically attractable carrier particles into a brushlike configuration. This

"magnetic brush" is engaged with the electrostatic image bearing surface and the toner particles are drawn from the brush to the latent image by electrostatic attraction.

5 Still another technique for developing electrostatic latent images is the "powder cloud" process as disclosed, for example, by C. F. Carlson in U.S. Patent 2,221,776. 10 In this method, a developer material comprising electrically charged toner particles in a gaseous fluid is passed adjacent the surface bearing the electrostatic latent image. The toner particles are drawn by 15 electrostatic attraction from the gas to the latent image. This process is particularly useful in continuous tone development.

Other development methods such as "touchdown" development as disclosed by 20 R. W. Gundlach in U.S. Patent 3,166,432 may be used where suitable.

Generally, commercial electrostatographic development systems utilize automatic machines. Since automatic electrostatographic imaging machines should 25 operate with a minimum of maintenance, the developer employed in the machines should be capable of being recycled through many thousands of cycles. In 30 automatic xerographic equipment, it is conventional to employ an electrophotographic plate which is charged, exposed and then developed by contact with a developer mixture. In some automatic machines, the 35 toner image formed on the electrophotographic plate is transferred to a receiving surface and the electrophotographic plate is then cleaned for reuse. Transfer is effected by a corona generating device 40 which imparts an electrostatic charge to attract the powder from the electrophotographic plate to the recording surface. The polarity of charge required to effect image transfer is dependent upon the 45 visual form of the original copy relative to the reproduction and to the electroscopic characteristics of the developing material employed to effect development. For example, where a positive reproduction is to 50 be made of the positive original, it is conventional to employ a positive corona to effect transfer of a negatively charged toner image to the recording surface. When a positive reproduction from a negative 55 original is desired, it is conventional to employ positively charged toner which is repelled by the charged areas on the plate to the discharged areas thereon to form a positive image which may be transferred by 60 negative polarity corona. In either case, a residual powder image usually remains on the image after transfer. Because the plate may be reused for a subsequent cycle, it is necessary that the residual image be removed to prevent "ghost images" from forming on subsequent copies and toner film from forming on the photoreceptor surface.

In a positive to positive reproduction process described above, the residual powder is tightly retained on the plate surface 70 by a phenomenon not fully understood which prevents complete transfer of the powder to the support surface, particularly in the image area. Incomplete transfer of toner particles is undesirable because 75 image density of the ultimate copy is reduced and highly abrasive photoreceptor cleaning techniques are required to remove the residual toner from the photoreceptor surface. This imaging process is ordinarily 80 repeated for each copy reproduced by the machine any time during the reusable life of the developer and the electrophotographic plate surface.

Various electrostatographic plate cleaning devices such as the "brush" and the 85 "web" cleaning apparatus are known in the prior art. A typical brush cleaning apparatus is disclosed by L. E. Walkup et al in U.S. Patent 2,832,977. The brush type 90 cleaning means usually comprises one or more rotating brushes, which remove residual powder from the plate into a stream of air which is exhausted through a filtering system. A typical web cleaning device 95 is disclosed by W. E. Graff, Jr. et al in U.S. Patent 3,186,838. As disclosed by Graff, Jr. et al, removal of the residual powder on the plate is effected by passing a web of fibrous materials over the plate surface. 100 Another system for removing residual toner particles from the surface of a photoreceptor comprises a flexible cleaning blade which wipes or scrapes the residual toner from the photoreceptor surface as the surface moves past the blade. 105

Unfortunately, the foregoing cleaning systems do not effectively remove all types of toner particles from all types of reusable photoreceptors. This is not a shortcoming 110 of the cleaning system, but a shortcoming of particular toners used in conjunction with particular photoreceptors. If a particular toner would not tend to form an adherent residual film on a particular 115 photoreceptor, the cleaning systems described would effectively remove all residual toner. However, many commercial toners of their very nature do tend to form a residual film on reusable photoreceptors. 120 The formation of such films is undesirable because it adversely affects the quality of undeveloped and developed images. The toner film problem of these particular 125 toners is acute in high speed copying and duplicating machines where contact between the developer and the imaging surface occurs a great many more times and at a higher velocity than in conventional electrostatographic systems. Ultimately, the 130

toner buildup becomes so great that effective copying or duplicating is impaired. As a result, more stringent means, e.g. solvent removal, are necessary to remove this type of film. Frequent shutdown of the apparatus, in order to clean the surface of the photoreceptor is obviously undesirable since the machine is taken out of commission and repeated techniques of this type wear down the photoreceptor surface.

Thus, there is a continuing need for a technique for eliminating the buildup of toner film on the surface of a photoreceptor. Electrostaticographic systems and, in particular, the imaging, developing and cleaning aspects of such systems would be significantly advanced if the foregoing problems were effectively overcome.

Accordingly, it is an object of the invention to provide a developer composition which effectively eliminates toner film buildup.

It is another object of the invention to provide a developer composition which improves solid area print density.

It is a further object of the invention to provide a developer composition which reduces background density of copies.

It is yet another object of the invention to provide a developer composition having enhanced and stabilized triboelectric characteristics.

It is still another object of the invention to provide a developer composition which permits effective long term prevention or control of toner filming on a reusable photoreceptor.

A still further object of the invention is to provide a developer composition of increased life, i.e., more prints per unit weight of developer.

Still another object of the invention is to provide a developer composition which yields copies of comparatively high optical density.

It is another object of the invention to provide a process which prevents undesirable buildup of developer components on reusable electrostaticographic imaging surfaces.

It is a further object of this invention to provide an electrostaticographic imaging process employing developing materials which provides for more effective cleaning of reusable electrostaticographic imaging surfaces.

It is another object of this invention to provide an electrostaticographic imaging process employing developer mixtures which are readily transferable from an electrostaticographic surface to a transfer surface.

A further object of the invention is to provide an improved developer composition and process which yields images

and copy with no loss of resolution.

Yet a further object is to provide an improved developer composition and process with no loss in fusing efficiency.

A still further object of the invention is to provide an improved developer composition having less tendency for toner blocking.

A further object of the invention is to provide an improved developer composition which increases the life of imaging surface cleaning members.

The present invention provides an electrostaticographic developing material in accordance with Claim 1 appended hereto, and a process of developing an electrostatic latent image in accordance with Claim 9 appended hereto. Preferences for this process and the developing material are given in the remaining appended claims.

The toner material of the present invention may be any electrosopic toner material which preferably is pigmented or dyed. Typical toner materials include polystyrene resin, acrylic resin, polyethylene resin, polyvinyl chloride resin, polyacrylamide resin, methacrylate resin, polyethylene terephthalate resin, polyamide resin, and copolymers, polyblends and mixtures thereof. Vinyl resins having a melting point or melting range starting at 110°F are especially suitable for use in the toner of this invention. These vinyl resins may be a homopolymer or a copolymer of two or more vinyl monomers. Typical monomeric units which may be employed to form vinyl polymers include: styrene; vinyl naphthalene; mono-olefins, such as ethylene, propylene, butylene, or isobutylene; vinyl esters, such as vinyl acetate, vinyl propionate, vinyl benzoate, or vinyl butyrate, esters of aliphatic methylene aliphatic monocarboxylic acids such as methyl acrylate, ethyl acrylate, n-butyl acrylate, isobutyl acrylate, dodecyl acrylate, n-octyl acrylate, methyl methacrylate, ethyl methacrylate or butyl methacrylate; vinyl ethers such as vinyl methyl ether, vinyl isobutyl ether, or vinyl ethyl ether; vinyl ketones such as vinyl methyl ketone, vinyl hexyl ketone or methyl isopropenyl ketone; and mixtures thereof. Suitable materials employed as the toner will usually have an average molecular weight between 3,000 to 500,000.

Any suitable pigment or dye may be employed as the colorant for the toner particles. Toner colorants are well known and include, for example, carbon black, nigrosine dye, aniline blue, Calco Oil Blue, chrome yellow, ultramarine blue, duPont Oil Red, quinoline yellow, methylene blue chloride, phthalocyanine blue, Malachite Green Oxalate, lamp black, Rose Bengal and mixtures thereof. The pigment or dyes

should be present in the toner in a sufficient quantity to render it highly coloured so that it will form a clearly visible image on a recording member. Thus, for example, where xerographic copies of typed documents are desired, the toner may comprise a black pigment such as carbon black or a black dye such as Amaplast Black Dye available from the National Aniline Products, Incorporated. Preferably, the pigment is employed in an amount of from 1% to 30%, by weight, based on the total weight of the colored toner. If the toner colorant employed is a dye, substantially smaller quantities of the colorant may be used.

When the toner materials of the present invention are to be employed in the aforementioned development processes, the toner should have an average particle size by weight percent less than 30 microns.

The metal salt of a fatty acid is capable of forming an adherent film deposit on the imaging surface of a reusable photo-receptor during the repeating cycles of an electrostatographic system. This salt need not be one which will form a completely continuous film on the imaging surface, although many will form a continuous film. Other metal salts of fatty acids will tend to fill the valleys of the surface and minute peaks will be coated with no more than a monolayer of the salt. The melting point of the metal salt is limited mainly by the ambient operating conditions and obviously should be at least somewhat higher than the ambient temperature.

The metal salts may be salts of saturated or unsaturated, substituted or unsubstituted fatty acids, preferably of from 8 to 35 carbon atoms. The metal salts of the above identified fatty acids include, but are not limited to, the lithium, sodium, potassium, copper, rubidium, silver, magnesium, calcium, zinc, strontium, cadmium, barium, mercury, aluminum, chromium, tin, titanium, zirconium, lead, manganese, iron, cobalt and nickel salts and mixtures of said salts. Specific fatty acids contemplated include caprylic, pelargonic, capric, undecanoic, lauric, tridecanoic, myristic, pentadecanoic, palmitic, margaric, stearic, arachidic, behenic, lignoceric, cerotic and mixtures thereof.

When a developer composition containing a metal salt of a fatty acid as the additive is employed for general copying purposes, there is noted an excessive buildup of this additive on the imaging surface in somewhat the same fashion as toner without an additive builds up. This buildup is also particularly acute in high speed copying and duplicating machines where contact between the developer and the imaging surface occurs a great many more

times and at higher velocities than in conventional electrostatographic systems. It was discovered that the utilization of modified silicon dioxide particles as specified in claim 1 appended hereto could be employed in conjunction with the friction-reducing material with outstanding success.

With no intention of being bound by any theory of action, it is believed that a metal salt of a fatty acid, if used as the sole developer additive, forms a lubricating film on an imaging surface more easily and to the essential exclusion of a toner film. This film not only permits more effective removal of residual toner material but also increases the life and efficiency of any cleaning member used to remove residual developer. During use, however, the metal salt of a fatty acid will build up to an extent which gradually degrades the quality of copies. By including in the developer composition a minor proportion of modified silicon dioxide particles as specified in claim 1 appended hereto, this material will control the buildup of the metal salt of a fatty acid by its abrasive action when a cleaning means removes residual developer from an imaging surface with a force which causes the developer mixture to be wiped across at least a portion of the imaging surface. This combination of additives permits the metal salt of a fatty acid to perform its function while the abrasive material prevents an excessive, interference layer of lubricant from building up. In addition, the proper triboelectric difference between a charging means, e.g. carrier particles, and the toner material is at least stabilized since the modified silicon dioxide particles specified in claim 1 appended hereto prevent a nullifying buildup of toner on the charging means.

Preferred modified silicon dioxide particles specified in claim 1 appended hereto are prepared by reacting freshly prepared colloidal silica with at least one organosilicon compound having organic groups as well as hydrolyzable groups attached to its silicon atom. In one technique, the reactants and steam are pneumatically introduced in parallel flow into a fluidized bed reactor heated to substantially 400°C. The organosilicon compound reacts with silanol groups on the surface of the SiO₂ particles and chemical attachment between the silicon atom in the organosilicon compound and the silicon atom in the SiO₂ occurs through an oxygen atom. Any suitable organic group directly attached to a silicon atom in the organosilicon compound may be employed in preparing the modified silica. The organic group is preferably one which imparts hydrophobic characteristics to the abrasive material to improve the stability of

developer materials under varying humidity conditions. The organic groups may comprise saturated or unsaturated substituted or unsubstituted hydrocarbon groups or derivatives thereof. Saturated organic groups include methyl, ethyl, propyl, butyl, chloropropyl and chloromethyl groups. Examples of typical organosilicon compounds include: dimethyl dichlorosilane, trimethyl chlorosilane, methyl trichlorosilane, vinyl triethoxy silane. The type of organo groups can influence the triboelectric characteristics of the developer. For example, silica treated with aminopropylsilane can be used in a reversal type developer.

The average particle size of the modified silicon dioxide particles additive should preferably fall within the submicron range of from substantially 1 to substantially 500 millimicrons and most preferably, between substantially 10 to substantially 100 millimicrons.

There is no particular criticality surrounding the shape of each said modified silicon dioxide particle since both spherical and irregularly shaped particles function effectively. A preferred material is Aerosil R972, a hydrophobic silica available from DeGussa Incorporated, New York, New York. "Aerosil" is a registered trademark.

The composition of the present invention finds utility in all known electrostatographic development systems. This includes systems which employ a carrier material such as magnetic brush development and cascade development as well as systems which do not necessarily employ a carrier material such as powder cloud development, fiber brush development and touchdown development.

Suitable coated and uncoated carrier materials for cascade development are well known in the art. The carrier particles comprise any suitable solid material, provided that the carrier particles acquire a charge having an opposite polarity to that of the toner particles when brought in contact with the toner particles so that the toner particles cling to and surround the carrier particles. When a positive reproduction of the electrostatic images is desired, the carrier particles are selected so that the toner particles acquire a charge having a polarity opposite to that of the electrostatic image. Alternatively, if a reversal reproduction of the electrostatic image is desired, the carrier is selected so that the toner particles acquire a charge having the same polarity as that of the electrostatic image. Thus, the materials for the carrier particles are selected in accordance with its triboelectric properties in respect to the electroscopic toner so that when mixed or brought into mutual contact, one component of the developer is charged positively if the other

component is below the first component in a triboelectric series and negatively if the other component is above the first component in a triboelectric series. By proper selection of materials in accordance with their triboelectric effects, the polarities of their charge, when mixed, are such that the electroscopic toner particles adhere to and are coated on the surface of carrier particles and also adhere to that portion of the electrostatic image bearing surface having a greater attraction for the toner than the carrier particles. Typical carriers include: steel, flintshot, aluminum potassium chloride, Rochelle salt, nickel, potassium chlorate, granular zircon, granular silica, methyl methacrylate, or glass. The carriers may be employed with or without a coating. Many of the foregoing and other typical carriers are described in U.S. Patent 2,618,552. An ultimate coated particle diameter between 50 microns to 2000 microns is preferred because the carrier particles then possess sufficient density and inertia to avoid adherence to the electrostatic images during the cascade development process. Adherence of carrier beads to electrostatic drums is undesirable because of the formation of deep scratches on the surface during the image transfer and drum cleaning steps. Also, print deletion occurs when large carrier beads adhere to xerographic imaging surfaces. For magnetic brush development, carrier particles having an average particle size less than 800 microns are satisfactory. Generally speaking, satisfactory results are obtained when 1 part toner is used with 10 to 1000 parts by weight of carrier in the cascade and magnetic brush developers.

Concerning the broad relative proportions of the toner material versus the additive materials, functionally stated, the metal salt of a fatty acid should be present in a proportion at least sufficient to form on adherent deposit substantially uniformly distributed over at least 20% of the area of an imaging surface during cyclic use of the imaging surface. It is preferred, that 100% of the imaging area becomes coated with the metal salt of a fatty acid. It has been found that from 0.01 to 10% by weight of a metal salt of a fatty acid based on the weight of the toner material will achieve the foregoing degree of coverage. A particularly preferred ratio is from 0.1% to 2.0% by weight of metal salt based on the weight of toner.

Functionally stated, the modified silicon dioxide particles specified in claim 1 appended hereto must be present in a relative proportion sufficient to maintain the thickness of the metal salt film deposit within the submicron range i.e. less than 10,000Å, in

order to avoid having an interference film, yet this proportion must not be so great as to completely remove the deposit or prevent one from forming. If the relative proportion is so great that no film is retained or formed, the modified silicon dioxide particles recited in claim 1 appended hereto will be acting directly on the photoreceptor and for long term operation this can contribute to shortening the life of the photoreceptor and certain of the cleaning means employed in the system. As a lower limit, as long as 5Å of the metal salt is available on the imaging surface the benefits of the present invention will be realized. One skilled in the art can readily determine optimum ratios of the dual additives by monitoring the thickness of the residual friction-reducing film. The use of a radioactive tracer in the metal salt is one effective means of optimizing proportions. Comparative long term runs will also be of assistance. Generally, it has been found that from 0.01% to .10% by weight of modified silicon dioxide particles specified in claim 1 appended hereto based on the weight of the toner material will achieve the desired results. A particularly preferred range is from 0.1 to 2.0% by weight.

The developing material of the present invention may be employed to develop electrostatic latent images on any suitable electrostatic latent image bearing surface including photoconductive surfaces. Well known photoconductive materials include: vitreous selenium, organic or inorganic photoconductors embedded in a non-photoconductive matrix, organic or inorganic photoconductors embedded in a photoconductive matrix. Representative patents in which photoconductive materials are disclosed include: U.S. Patent 2,803,542 to Ullrich, U.S. Patent 2,970,906 to Bixby, U.S. Patent 3,121,006 to Middleton, U.S. Patent 3,121,007 to Middleton and U.S. Patent 3,151,982 to Corrsin.

In U.S. Patent 2,986,521, Wielicki, there is taught a reversal type developer powder for electrostatic printing comprising electroscopic material, i.e. toner, coated with a finely divided colloidal silica. The toner material must have (1) a positive triboelectric relationship with respect to the silica and (2) the silica coated toner must be repelled from negatively charged areas of an imaging surface. The only positively stated purpose or utility for the silica is to reduce tackiness and improve the free flowing characteristics of the developer powder.

In British Patent Specification No. 1,172,839 it is taught that the inclusion of a minor proportion of hydrophobic metal salt of a fatty acid in an electrostatic developer overcomes certain problems as-

sociated with the use of prior art toner and carrier materials. Among the problems are the tendency of the toner to form unwanted deposits which interfere with copy quality and the long term abrasive affects of carriers and some toners. The metal salt of a fatty acid overcomes these problems, however, it has been observed that excessive buildup of the metal salt can likewise cause degradation of copy quality.

In U.S. Patent 3,552,850 issued to Stephen F. Royka et al, it is taught to employ a dry lubricant when employing a blade cleaner in an electrostatographic imaging system. This patent, however, does not teach how to control the deleterious buildup of dry lubricant.

The following examples further define, describe and compare exemplary methods of preparing the development system components of the present invention and of utilizing them in a development and cleaning process. Parts and percentages are by weight unless otherwise indicated. The examples, other than the control examples, are also intended to illustrate the various preferred embodiments of the present invention.

EXAMPLE I

The vitreous selenium drum of an automatic copying machine is corona charged to a positive voltage of 800 volts and exposed to a light and shadow image to form an electrostatic latent image. The selenium drum is then rotated through a magnetic brush development station. A control developer comprising 2 parts of toner, containing a polystyrene resin and 100 parts of steel shot carrier beads. The toner particles have an average particle size of 12 microns and the carrier beads an average particle size of 125 microns. After the electrostatic latent image is developed in the developing station, the resulting toner image is transferred to a sheet of paper at a transfer station. The residual toner particles remaining on the selenium drum after passage through the transfer station is removed by three different techniques. In each case, and in subsequent examples, it is to be understood that a clean selenium drum is employed in the examples.

One technique employs a cylindrical brush having an overall diameter of 4 inches, a 15 denier polypropylene having a pile height of 3/8 inch, and a fiber density of 54,000 fibers per square inch. The brush is positioned against the drum to permit a fiber interference of 0.1 inch and is rotated at 175 revolutions per minute. Initial copy quality is excellent, however, after 25,000 copies, background density is very high, resolution is markedly decreased, image fill

in solid and line copy is poor and edge definition is poor. Inspection of the drum reveals slight signs of wear and a significant buildup of toner on the surface thereof.

A second technique employs a cleaning web of the type disclosed by W. P. Graff, Jr. et al in U.S. Patent 3,186,838. A non-woven rayon web contact pressure of 18 pounds per square inch, web-photoreceptor relative speed of 1.5 inches per second, and a web contact arc distance of 1/8 inch are employed. After the copying process is repeated 5000 times, the copies show fairly good line contrast and little background deposit. However, large solid areas possess a washed out appearance. Micrograph studies of the drum surface reveal a significant buildup of toner film.

A third technique employs a doctor blade cleaning mode of removing residual toner. A rectangular 1/16 inch thick strip of elastomeric polyurethane material, having one end chamfered to form a cleaning edge having an angle of 60°, is positioned parallel to the axis of the drum. The chamfered edge of the blade is held at a chiseling rather than wiping attitude with respect to the moving drum. The vertical resultant force employed to press the entire blade edge against the drum surface is about three pounds as read on a spring scale. Initial copies reveal good copy quality in all respects, however, after 2000 copies, image quality is markedly inferior showing high background density, poor image fill and decreased resolution. Inspection of the drum reveals a significant buildup of toner on the imaging surface.

The foregoing illustrates the problem encountered when employing a typical toner material which of its very nature has a tendency to build up on the photoreceptor. The increasing buildup is undoubtedly the main cause of decline in copy quality.

EXAMPLE II

The developer procedure of Example I is repeated except that the developer is modified in the following manner: 0.1 part of zinc stearate having a particle size distribution of 0.75 to 40.0 microns is gently folded into one part of toner. The resulting mixture is thoroughly milled in a Szegvari attritor for 10 minutes. After developed image transfer, as in Example I, the doctor blade and technique of Example I is employed except the blade force used is 0.2 pounds. After 2000 cycles, the copies are characterized by high density and high background deposits. The surface of the selenium drum will be observed to have an excessive film buildup. The film deposit is either zinc stearate or a combination of the same with toner.

By increasing the blade force on the

photoreceptor drum to three pounds copy quality remained good through 2000 cycles.

The foregoing example illustrates that by employing a representative friction-reducing material, i.e., zinc stearate, in the developer composition, coupled with a cleaning means supplying sufficient force during cleaning, deleterious film buildup is effectively controlled.

The following examples illustrate that by employing a comparatively abrasive material in conjunction with the film forming lubricant, copies of exceptionally high quality are obtained by an even more effective control of film buildup.

EXAMPLE III

The developing procedure of Example I is repeated except that the developer is modified in the following manner: To the toner of Example I, 0.25% of zinc stearate is added and milled in a Szegvari attritor for ten minutes. Thereafter, 1.0% by weight of a treated submicron silicon dioxide is added and milled for an additional ten minutes. The treated silicon dioxide particles are produced by flame hydrolysis decomposition of pure silicon tetrachloride in the gaseous phase in an oxyhydrogen flame at about 1100°C followed by reaction in a heated fluidized bed reactor with dimethyl dichlorosilane. 75% of the silanol groups present on the surface of the freshly prepared silicon dioxide particles are reacted with the silane in the fluidized bed reactor. The silicon dioxide particles have 3 silanol groups per 100Å² of a surface prior to reaction with silane. Analysis of the final product reveals 99.8% SiO₂ and the balance carbon, Cl, heavy metals, Fe₂O₃, Al₂O₃, TiO₂ and Na₂O₃. The particle size is between 10-30 millimicrons and the surface area is 90-150 m²/g.

The relative coefficient of friction values for the several materials, determined by the technique described above, are as follows. Selenium 5.23, toner 3.92 and zinc stearate 0.67. The toner has a Shore Durometer hardness of greater than 100 on the A and B scale, zinc stearate 66 on the A scale and 52 on the B scale. The treated silicon dioxide has a hardness of 5 on Moh's scale. After developed image transfer as in Example I, the blade cleaning technique of Example I is employed utilizing a blade force of 3 pounds. After 2000 cycles, the copies are characterized by the same exceptionally high image quality as the initial copies. Inspection of the selenium drum will reveal a film buildup of less than 300Å.

EXAMPLE IV

The process of Example III is repeated except the dual additive consists of 0.25% zinc stearate and 1.0% untreated submicron silicon dioxide. The silicon dioxide

is identical to that of Example III except it is not treated to render it organophilic. The process is operated at a relative humidity of 80% at an average temperature of 75°F. The background density, resolution, image fill in line copies and edge definition are good in initial copies. However, after 900 copies, background density has more than doubled, resolution has decreased, image-fill in line copies is poor and edge-definition is poor. The photoreceptor reveals a dull damp claylike film which cannot be removed by ordinary cleaning techniques.

The same process carried out at a relative humidity of 30% at 75°F yields excellent copies after 2000 cycles. No claylike film is observed on the photoreceptor surface.

When the treated silicon dioxide of Example III is employed in the composition under the high relative humidity condition of 80% at 75°F image quality remains excellent and no colloidal silica deposit is observed on the photoreceptor.

It is believed that the voluminous, high surface area, untreated silica acts as desiccant and the water taken up by the additive deleteriously affects all aspects of the development and cleaning steps of the process. Under comparatively dry conditions this is not observed.

EXAMPLE V

The developing procedure of Example III is repeated except instead of zinc stearate, 0.25% of copper stearate is employed. After 2000 cycles, this developer yields copies of good quality in every respect. The film buildup on the photoreceptor does not exceed 300Å.

Although specific materials and conditions are set forth in the foregoing examples, these are merely intended as illustrations of the present invention. Various other suitable toner components, additives, colorants, carriers and development techniques such as those listed above may be substituted for those in the examples with similar results. Other materials may also be added to the toner or carrier to sensitize, synergize or otherwise improve the imaging properties or other desirable properties of the system.

Reference is made to our copending British patent application 46890/72 (Serial No. 1 402 009).

WHAT WE CLAIM IS:—

1. An electrostatographic developing material comprising particles, said particles including (1) divided electroscopic toner material; (2) 0.01 to 10.0 percent by weight based on the weight of said toner material of a metal salt of a fatty acid; and (3) 0.01 to 10.0 per cent by weight based on the weight of said toner material of submicron

size colloidal particles that are silicon dioxide particles having surface silicon atoms chemically attached through silicon-oxygen-silicon bonding to silicon atoms having 1 to 3 organic groups directly attached thereto by silicon-carbon bonding.

2. The developing material of Claim 1 wherein said metal salt is zinc stearate.

3. The developing material of Claim 1 or 2 wherein said metal salt is present in from 0.1 percent to 2.0 percent by weight based on the weight of said toner; and said modified silicon dioxide particles are present in from 0.1 percent to 2.0 percent by weight based on the weight of said toner material.

4. The developing material of any one of claims 1 to 3 wherein said modified silicon dioxide particles have an average particle size of 1 to 500 millimicrons.

5. The developing material of Claim 4 wherein said average particle size is 10 to 100 millimicrons.

6. The developing material of Claim 4 wherein said average particle size is less than 30 microns.

7. The developer material of any of Claims 1 to 6 including from 10-1000 parts by weight of carrier particles per part of toner material, said carrier particles being larger than said divided-toner material.

8. The developing material of claim 1, substantially as described with reference to the Examples.

9. A process of developing an electrostatic latent image comprised by a surface, said process comprising

developing an electrostatic latent image by the developing material of any one of Claims 1 to 8, to give a developed image corresponding to said latent image.

10. The process of Claim 9, comprising removing at least a portion of at least any residual developed image from said surface by a force which causes the toner, metal salt and said modified silicon dioxide particles of said developing material to be wiped across at least a portion of said surface.

11. The process of Claim 10 wherein the combination of said force and the abrasive character of said modified silicon dioxide particles is sufficient to maintain the buildup of said metal salt on said imaging surface in the submicron range without completely removing said buildup.

12. The imaging process of Claim 10 or 11 wherein said force is applied via a cleaning blade.

13. The imaging process of Claim 10 or 11 wherein said force is applied via a cleaning web.

14. The imaging process of Claim 10 or 11 wherein said force is applied via a cleaning brush.

15. The process of any one of Claims 130.

10 to 14, comprising repeating the process sequence at least one time.

16. The process of Claim 9, substantially as described with reference to the 5 Examples.

For the Applicant(s):—
A. POOLE & CO.,
Chartered Patent Agents,
54 New Cavendish Street,
London, W1M 8HP.

Printed for Her Majesty's Stationery Office by The Tweeddale Press Ltd., Berwick-upon-Tweed, 1975.
Published at the Patent Office, 25 Southampton Buildings, London, WC2A 1AY, from which copies may be obtained.